



**KONGSBERG**  
AUTOMOTIVE

# UltiFlex®

FLUID TRANSFER SYSTEMS



## PROPERTIES

APPLICATION	FOR ANY INDUSTRY – PHARMACEUTICAL, BIO-TECH, FOOD & BEVERAGE, CHEMICAL, PETRO-CHEMICAL, GENERAL PURPOSE INDUSTRIAL, AUTOMOTIVE OE & AUTOSPORT
DESIGN	1/2" - 2" PATENTED MANUFACTURE OF SMOOTHBORE, CONVOLUTED PTFE HOSE CONSTRUCTION
INNER LAYER	FDA APPROVED VIRGIN OR ANTI-STATIC PTFE TUBE
OUTER LAYER	1/2" - 2" 304SS BRAID
TEMPERATURE MIN/MAX	-60°C TO +260°C (-76°F TO +500°F)
MATERIAL	PTFE ACCORDING TO: "ASTM D4895, TYPE 1, GRADE 4, CLASS B"
CERTIFICATION	IN COMPLIANCE; FDA, EU FOOD, USP CLASS VI, ANTI-STATIC (AS), EN:16643 & MATERIAL CERTIFICATION

## PRODUCT DESCRIPTION

UltiFlex® – Ultra-flexible, smoothbore PTFE hose range. When space is an issue, but a smoothbore is a must for an uninterrupted flow and ease of cleaning. Also for arduous applications where strength and resilience coupled with PTFE's unique qualities are required. Bespoke UltiFlex® PTFE hose assemblies are available directly from KA with non-lined or lined (Tafted / Flared) end fittings to improve cleanliness, remove or reduce bug traps and improve the ability to clean in place (CIP) & Sterilize in Place (SIP).



**EUROPE:** FOXBRIDGE WAY, NORMANTON, WEST YORKSHIRE, WF6 1TN, UNITED KINGDOM // T: +44 1924 228000

**NORTH AMERICA:** ONE FIRESTONE DRIVE, SUFFIELD, CT 06078, UNITED STATES // T: +1 860 668 1285

**CHINA:** NO.30 & 32, XIKUNRD, WUXI SINGAPORE IND. PARK, WUXI, JIANGSU PROVINCE P.R CHINA, 214028 // T: +86 510 8528 5903

**YOUR FLEXIBLE PTFE HOSE PARTNER // WWW.KAHOSE.COM**



## UltiFlex®

PART NUMBER	DESCRIPTION	ID NOMINAL		OD NOMINAL		TUBE WALL THICKNESS NOM.		MAX. WORKING PRESSURE		MIN. BURST PRESSURE		MIN. BEND RADIUS		FORCE TO BEND		WEIGHT	
		mm	in	mm	in	mm	in	psi	bar	psi	bar	mm	in	kg	lbs	kg/m	lb/ft
SBC12-0B01	1/2" Ultiflex®	13,40	0,53	18,00	0,71	1,60	0,06	870	60,00	3481	240	38,00	1,50	5,00	11,00	0,26	0,18
SBC20-0B01	3/4" Ultiflex®	19,10	0,75	24,10	0,95	1,80	0,07	870	60,00	3481	240	50,00	1,97	5,00	11,00	0,42	0,28
SBC22-0B01	7/8" Ultiflex®	21,00	0,83	27,00	1,06	2,10	0,08	798	55,00	3191	220	55,00	2,17	6,50	11,00	0,50	0,34
SBC25-0B01	1" Ultiflex®	25,50	1,00	31,40	1,24	2,20	0,09	725	50,00	2901	200	70,00	2,76	7,00	11,00	0,64	0,43
SBC32-0B01	1 1/4" Ultiflex®	31,80	1,25	39,30	1,55	2,65	0,10	653	45,00	2611	180	100,00	3,94	8,50	11,00	0,90	0,60
SBC40-0B01	1 1/2" Ultiflex®	38,10	1,50	46,10	1,81	3,00	0,12	580	40,00	2321	160	140,00	5,51	13,50	11,00	1,18	0,79
SBC50-0B01	2" UltiFlex®	49,50	1,95	58,20	2,29	3,00	0,12	435	30,00	1740	120	280,00	11,02	20,00	44,00	1,72	1,15

## UltiFlex® Conductive

PART NUMBER	DESCRIPTION	ID NOMINAL		OD NOMINAL		TUBE WALL THICKNESS NOM.		MAX. WORKING PRESSURE		MIN. BURST PRESSURE		MIN. BEND RADIUS		FORCE TO BEND		WEIGHT	
		mm	in	mm	in	mm	in	psi	bar	psi	bar	mm	in	kg	lbs	kg/m	lb/ft
SBCF12-0B01	1/2" Ultiflex® AS	13,40	0,53	18,00	0,71	1,60	0,06	870	60,00	3481	240	38	1,50	5,00	11	0,26	0,18
SBCF20-0B01	3/4" Ultiflex® AS	19,10	0,75	24,10	0,95	1,80	0,07	870	60,00	3481	240	50	1,97	5,00	11	0,42	0,28
SBCF22-0B01	7/8" Ultiflex® AS	21,00	0,83	27,00	1,06	2,10	0,08	798	55,00	3191	220	55	2,17	6,50	14	0,50	0,34
SBCF25-0B01	1" Ultiflex® AS	25,50	1,00	31,40	1,24	2,20	0,09	725	50,00	2901	200	70	2,76	7,00	15	0,64	0,43
SBCF32-0B01	1 1/4" Ultiflex® AS	31,80	1,25	39,30	1,55	2,65	0,10	653	45,00	2611	180	100	3,94	8,50	19	0,90	0,60
SBCF40-0B01	1 1/2" Ultiflex® AS	38,10	1,50	46,10	1,81	3,00	0,12	580	40,00	2321	160	140	5,51	13,50	30	1,18	0,79
SBCF50-0B01	2" UltiFlex® AS	49,50	1,95	58,20	2,29	3,00	0,12	435	30,00	1740	120	280	11,02	20,0	44	1,72	1,15

